

Version No. 2	Page 1 of 4	<div>Technical Definition</div> <div>Compression AITM 1-0008 A2 (Thin) test Carbon Fiber Composite</div>
<div>ptp.</div>		
<div>Kit 31-6-2023</div> <div>Compression A2</div>		

You shall respect the HSE policy of your laboratory for each performed test.

Instructions to participant laboratories

Please read these instructions carefully BEFORE starting the tests.


1. Five specimens (152 x 22 x 2,9 mm) are supplied to each participant – 5 results must be provided.
If one result is missing, your test will be considered as an outlier. A RCA shall be completed.
2. The specimens have to be dried during 48 hours (0/+10) at 70°C (+/- 3) and tested within the next 8 hours after the drying.
3. Prerequisite for starting the tests are:
 - an Airbus qualification for this test
 - For laboratories which are not qualified yet, the rules of Technical Qualification of Mechanical Test Methods apply. The PTP kit may be used for the required comparison tests.
4. All tests must be performed at room temperature in accordance with the requirements of **AITM 1-0008 issue 08**. The conformity of the specimens to the requirements of AITM 1-0008 shall be verified before testing.

The tests shall be performed respecting the following conditions:

- One operator only
- One testing machine only
- Tests performed in sequence

The use of the standard anti-buckling device is mandatory.

Version No. 2	Page 2 of 4	<div>Technical Definition</div> <div>Compression AITM 1-0008 A2 (Thin) test</div> <div>Carbon Fiber Composite</div>
<div>ptp.</div>		
<div>Kit 31-6-2023</div> <div>Compression A2</div>		



If necessary, the tab length can be adjusted. If you do so, particular care shall be taken on parallelism of edges.

5. The following information need to be reported:

Characteristic	Unit	Significant digits	Mandatory / Not mandatory	Evaluated Yes/no
Room Temperature	°C	XX,X	Mandatory	No
Ambient Humidity	%	XX,X	Mandatory	No
Specimen thickness	mm	X,XX	Mandatory	No
Specimen width	mm	X,XX	Mandatory	No
Percent Bending Stress	%	X,X	Mandatory	No
Compression strength	MPa	XXX,X	Mandatory	Yes
Compression modulus	GPa	XX,X	Mandatory	Yes
Failure mode	N/A	N/A	Mandatory	No
Upload of the official test report	N/A	N/A	Mandatory	No

All calculations shall be based on **nominal thickness**: 2,944 mm

All evaluated characteristics will be analysed according to the algorithm A and S (ISO 13528 – 2022) and evaluated using z-score.

6. Testing shall start **as soon as test specimens are received**. Please contact the following e-mail address for any technical or administrative query.

Version No. 2	Page 3 of 4	<div>Technical Definition</div> <div>Compression AITM 1-0008 A2 (Thin) test</div> <div>Carbon Fiber Composite</div>
<div>ptp.</div>		
<div>Kit 31-6-2023</div> <div>Compression A2</div>		

Submission date:	1st July, 2023
Technical and administrative support:	info@ptpscheme.com

7. Instructions for submission of results are detailed on the website:

<https://ptpscheme.com/>

8. To ensure the confidential treatment of your results in the final report, you will be allocated a unique identity number when you register for the program.
9. Collusion and falsification of your PTP results are totally forbidden. In case of identification or suspicion of collusion or falsification, the laboratory will be excluded from the program and the sponsors will be immediately informed. The sponsors could ask you proofs of your records and analyses, so be sure to conserve data, curves and specimens.
10. The tested specimens do not need to be sent back to PTP.

Note:

The following data shall be provided on demand:

- Pictures of failure mode (front and side view)
- Pictures of whole specimen after test
- Result table including all dimensions and results as required in AITM 1-0008
- Load-displacement curves
- Stress-strain curves for each specimen separately with curves for each strain gauge separately
- Detailed pictures of test set-up
- Specimen dimensional measurement [mm]
- Percent bending at 90% failure load

The following requirements regarding the results have to be met:

- Valid failure mode
- Failure within gauge length
- Load-displacement curve without any discontinuities
- Percent bending strain <10% between 10% and 90% of failure load
- No slipping of specimen in grips is allowed.

Version No. 2	Page 4 of 4	<div>Technical Definition</div> <div>Compression AITM 1-0008 A2 (Thin) test Carbon Fiber Composite</div>
<div>ptp.</div>		
<div>Kit 31-6-2023</div> <div>Compression A2</div>		

APPENDIX: Instructions for IRR participation

The Internal Round Robin participation (IRR) is **optional** and **independent** from your PTP participation. Confidentiality: The IRR results and reports are confidential and only accessible by your laboratory. They are not shared with the scheme sponsors or any other accreditation or certification bodies.

The extra samples shall be tested according to the following table:

	Operator 1	Operator 2	Operator 3	Operator 4	Operator X
Test machine 1	PTP kit (5 samples)	3 samples	3 samples	3 samples	3 samples
Test machine 2	3 samples				
Test machine 3	3 samples				
Test machine Y	3 samples				

Operator 1 (OP1) is to be the most experienced operator currently conducting tests on a regular basis and shall perform tests on all machines (TM1, TM2, TM3...)

Test Machine 1 (TM1) is to be the most utilised machine for this test in your laboratory and shall be tested by all operators (OP1, OP2, OP3...)

Example: A laboratory has 2 operators and 3 test machines. They receive a PTP kit and 9 extra specimens.

Operator 1 shall test the PTP kit on TM1, 3 specimens on TM2 and 3 specimens on TM3.

Operator 2 shall test 3 specimens on TM1.

The IRR results have to be submitted on a separate results form available on the PTP website.

The identification of operators and test machines you provide will appear on the IRR final report. These identifications will not be seen by other laboratories.

The IRR results will be classified against the acceptance classes of the kit Compression A2-2023.

Reminder: Laboratories are not permitted to switch specimens between the PTP kit and IRR samples. The traceability of the samples will be checked during the evaluation. Laboratories found to have switched samples will invalidate their PTP participation.

VERSION HISTORY

Issue Date	Issue N°	Changes
18/01/2023	1	Document creation
28/04/2023	2	Modification of the submission date